



---

## Product - Devcom Heavy Duty Ice & Water Weather-Defender™ - IW-DC4200

42 mil Thick – Self Adhered Ice & Water Protective Membrane – Clean & Green Patented Design Front to Back  
Smooth or Drizzle NON-SKID-COAT Designs Available – Water Tight Reflective Polyester Tac-Surface  
Zero VOC's/Solventless, Super-Agressive Hot Melt Adhesive, w/ Patented Tuck-n-Fin E-Z Release Liner  
7 Layer Construction w/ Hi-Strength Nonwoven Composite / Met-Polyester Reinforced Insulating Cores & Skins  
Highly Reflective/Super Energy Efficient/Low Emissivity  
Super High Strength w/ a Virtual Tear-Stretch-Shrink-Curl Proof Design  
Zero Light Transmission – 100% Opaque  
Recycled/Reclaimed Content – Fully Sustainable  
Standard Facer/Membrane Colors: Green, White (others available upon request)  
Personalized Logo Design on our Films featuring our Custom "Your Logo Here" Program  
Standard Adhesive Color/Tint: Clear

### Applicable Testing Procedures:

U.V. Protection: 48-60 Months  
Self Seal: ASTM D1970 Section 7.9 = Pass  
Advanced Aging: ASTM D750-68 @ 5000 hrs = No notable change in Membrane or Adhesive  
Low Temperature Flexibility: ASTM D1970 = Pass (Unaffected at -10 deg F)  
Adhesion to Plywood: ASTM D903 = 4.25 lbs/in width  
Tensile Strength MD in PSI: ASTM D882 = 1876/PSI  
Tensile Strength MD: ASTM D882 = 213 Lb/In-Width – TD: ASTM D882 = 239 Lb/In-Width  
Tear MD: ASTM D1922 = 5,712 Grams – TD: ASTM D1922 = 6,106 Grams  
Elongation at Break: ASTM D412 = 500% Minimum  
Puncture: ASTM E154 = 222 Lbs  
Water Vapor Transmission Rate: ASTM E 96-53 (Method E) = .0011 perms



***Made with Pride in the Heartland of the USA!***

#### Corporate Office

111 West Port Plaza Drive, Suite 600 / St. Louis, MO 63146  
**Corporate Office:** 866.DEVCOM1 (338.2661) / **Scott Ford (direct):** 503.849.4106 / **e:** sford@devcomtape.com / **w:** devcomtape.com